

Technical Data Sheet : AdvyForm R1001

Polypropylene, Random Copolymer

Product Description

The products is a controlled rheology medium modified propylene random copolymer for manufacturing high transparent cast films, contains no slip or anti-blocking agents and offers very good processability, excellent clarity and gloss and exhibits very good heat weldability.

Information regarding regulatory status, including supported, prohibited, or restricted applications, is provided in the **Product Regulatory Summary** and the **Safety Data Sheet (SDS)**.

General

Application	Food Packaging Film; Stationery Film; Textile Packaging Film
Market	Flexible Packaging
Processing Method	Cast Film
Attribute	Controlled Rheology; Good Processability; High Clarity; High Gloss; Random Copolymer; Weldable
Internal ref. number	1Q044, BEN8738
Revision	Version 2 ; September 4, 2026

Properties.

		Nominal	
		Value	Units
Physical			
Melt Flow Rate, (230 °C/2.16 kg)		8	g/10 min ISO 1133-1
Density		0.9	g/cm ³ ISO 1183-1
Mechanical			
Flexural Modulus		700	N/mm ² ISO 178
Tensile Stress at Break, (23 °C, 50 mm/min)		26	N/mm ² ISO 527-1, -2
Tensile Stress at Yield, (23 °C, 50 mm/min)		23	N/mm ² ISO 527-1, -2
Tensile Strain at Break, (23 °C, 50 mm/min)		600	% ISO 527-1, -2
Tensile Strain at Yield, (23 °C, 50 mm/min)		14	% ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)		10	kJ/m ² ISO 179-1/1eA
(0 °C, Type 1, Edgewise, Notch A)		3	kJ/m ² ISO 179-1/1eA
Thermal			
Vicat Softening Temperature, (A50)		125	°C ISO 306
Deflection Temperature Under Load, (0.46 N/mm ²)		60	°C ISO 75B-1, -2

*) These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.



Rotterdam Olefins & Polyolefins B.V.
Aert van Nesstraat 45, 3012 CA
Rotterdam, The Netherlands

Company Information

For further information regarding the Velogy, please visit <http://www.velogy.com>

© Rotterdam Olefins & Polyolefins B.V.

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, Velogy may further prohibit or restrict the sale of its products into certain applications.

For further information, please contact RegulatoryComplianceROP@velogy.com

Trademarks

The Trademark referenced within the product name is owned or used by the Velogy group of companies