

Technical Data Sheet : AdvyForm E0660

Polypropylene, Impact Copolymer

Product Description

The grade is a heterophasic copolymer with medium flow, used in extrusion and injection molding applications. This grade is nucleated and characterized by a medium stiffness-impact balance also at low temperature combined with low stress whitening. The additive formulation provides a good heat aging resistance. Is typically used by customers requiring a high resistance to temperature degradation, in particular for battery cases and automotive components.

Information regarding regulatory status, including supported, prohibited, or restricted applications, is provided in the **Product Regulatory Summary** and the **Safety Data Sheet (SDS)**.

General

Application	Battery Cases
Market	Automotive; Consumer Products; Industrial, Building & Construction
Processing Method	Injection Molding
Attribute	Good Heat Aging Resistance; Good Impact Resistance; Good Stiffness; Heat Stabilized; Impact Copolymer; Low Warpage
Internal ref. number	1Q095, BEN8424
Revision	Version 1.1 : June 2026

Properties.

Typical Properties		Nominal		
		Value		
Physical				
Melt Flow Rate, (230 °C/2.16 kg)		2	g/10 min	ISO 1133-1
Density		0.90	g/cm ³	ISO 1183-1
Mechanical				
Flexural Modulus		1350	MPa	ISO 178
Tensile Modulus		1300	MPa	ISO 527-1, -2
Tensile Stress at Break		7	MPa	ISO 527-1, -2
Tensile Stress at Yield		26	MPa	ISO 527-1, -2
Tensile Strain at Break		100	%	ISO 527-1, -2
Tensile Strain at Yield		8	%	ISO 527-1, -2
Impact				
Charpy Impact Strength – Notched				
(23 °C, Type 1, Edgewise, Notch A)		35	kJ/m ²	ISO 179
(-20 °C, Type 1, Edgewise, Notch A)		6	kJ/m ²	ISO 179
Thermal				
Vicat Softening Temperature, (A50)		149	°C	ISO 306
Deflection Temperature Under Load, (0.45 MPa, Unannealed)		88	°C	ISO 75B-1, -2

*)These are typical property values not to be construed as specification limits.

Processing Techniques

Users should determine the conditions necessary to obtain optimum product properties and suitability of the product for the intended application.

In cases where higher temperatures are required, please contact your appropriate technical contact for support.

Company Information

For further information regarding the Velogy, please visit <http://www.velogy.com>

© Rotterdam Olefins & Polyolefins B.V.

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, Velogy may further prohibit or restrict the sale of its products into certain applications.

For further information, please contact RegulatoryComplianceROP@velogy.com