

Technical Data Sheet : AdvyForm R0532

Polypropylene, Random Copolymer

Product Description

The polymer grade is a clarified random copolymer for extrusion applications. The grade exhibits excellent transparency, gloss and stiffness. Typically used by customers in extrusion blow moulding, sheet extrusion and thermoforming.

Information regarding regulatory status, including supported, prohibited, or restricted applications, is provided in the **Product Regulatory Summary** and the **Safety Data Sheet (SDS)**.

General

Applications	Bottles For Consumer Goods; Bottles for Industrial Use
Market	Industrial Packaging; Rigid Packaging
Processing Method	Extrusion Blow Molding; Sheet; Thermoforming
Attribute	High Gloss; High Transparency; Medium Stiffness; Nucleated; Random Copolymer
Internal ref. number	1Q184, BEN15553
Revision	Version 1.1 ; June 2026

Properties.

Typical Properties	Nominal Value*	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	1.8	g/10 min	ISO 1133-1
Density, (23 °C)	0.9	g/cm ³	ISO 1183-1
Mechanical			
Tensile Modulus	1050	MPa	ISO 527-1, -2
Tensile Stress at Yield	29	MPa	ISO 527-1, -2
Tensile Strain at Break	>50	%	ISO 527-1, -2
Tensile Strain at Yield	13	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	26	kJ/m ²	ISO 179
(0 °C, Type 1, Edgewise, Notch A)	3.5	kJ/m ²	ISO 179
Thermal			
Vicat Softening Temperature, (A50)	130	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	80	°C	ISO 75B-1, -2
Optical			
Haze, (1 mm - injection molded disc)	12	%	ASTM D1003

*)These are typical property values not to be construed as specification limits.

Processing Techniques

Users should determine the conditions necessary to obtain optimum product properties and suitability of the product for the intended application.

Company Information

For further information regarding the Velogy, please visit <http://www.velogy.com>

© Rotterdam Olefins & Polyolefins B.V.

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, Velogy may further prohibit or restrict the sale of its products into certain applications.

For further information, please contact RegulatoryComplianceROP@velogy.com