

Technical Data Sheet : AdvyForm P0409

Polypropylene, Homopolymer

Product Description

The polymer grade is a non-pelletized homopolymer powder. The product is non stabilized. When pelletized and additivated suitable for injection moulding and extrusion applications.

The main applications are mineral filled compounds, colour and additives masterbatches.

The properties reported below are measured on the pelletized and additivated resin.

Information regarding regulatory status, including supported, prohibited, or restricted applications, is provided in the **Product Regulatory Summary** and the **Safety Data Sheet (SDS)**.

General

Market	Compounding
Processing Method	Compounding
Internal ref. number	1Q058, BEN8552
Revision	Version 1.1 : june 2026

Properties.

Typical Properties	Nominal Value*	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	1.2	g/10 min	ISO 1133-1
Density	0.9	g/cm ³	ISO 1183-1
Mechanical			
Tensile Modulus, (23 °C)	1450	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C)	3.5	kJ/m ²	ISO 179
Thermal			
Vicat Softening Temperature, (A50)	153	°C	ISO 306

*)These are typical property values not to be construed as specification limits. Reported properties are measured on the pelletized and additivated resin.

Processing Techniques

Users should determine the conditions necessary to obtain optimum product properties and suitability of the product for the intended application.

In cases where higher temperatures are required, please contact your appropriate technical contact for support.



Rotterdam Olefins & Polyolefins B.V.
Aert van Nesstraat 45, 3012 CA
Rotterdam, The Netherlands

Company Information

For further information regarding the Velogy, please visit <http://www.velogy.com>

© Rotterdam Olefins & Polyolefins B.V.

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, Velogy may further prohibit or restrict the sale of its products into certain applications.

For further information, please contact RegulatoryComplianceROP@velogy.com