

Technical Data Sheet : KeyForm E1742

Polypropylene, Impact Copolymer

Product Description

The polymer grade is a fast crystallization heterophasic copolymer, suitable for injection molding applications, and contains an anti-static agent. It exhibits a high stiffness combined with a medium fluidity.

Can be used successfully in houseware, garden furniture, cylindrical containers for detergency and crates.

Information regarding regulatory status, including supported, prohibited, or restricted applications, is provided in the **Product Regulatory Summary** and the **Safety Data Sheet (SDS)**.

General

Application	Housewares; Opaque Containers; Sports, Leisure & Toys
Market	Consumer Products; Rigid Packaging
Processing Method	Injection Molding
Attribute	Contains Antistat; High Flow; Impact Copolymer; Nucleated
Internal ref. number	1Q196, BEN3028
Revision	April 2026

Properties.

Typical Properties	Nominal Value*	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	70	g/10 min	ISO 1133-1
Density	0.9	g/cm ³	ISO 1183-1
Mechanical			
Tensile Modulus	1260	MPa	ISO 527-1, -2
Tensile Stress at Yield	23	MPa	ISO 527-1, -2
Tensile Strain at Break	20	%	ISO 527-1, -2
Tensile Strain at Yield	4	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	9	kJ/m ²	ISO 179
(0 °C, Type 1, Edgewise, Notch A)	6	kJ/m ²	ISO 179
(-20 °C, Type 1, Edgewise, Notch A)	5	kJ/m ²	ISO 179
Ductile/Brittle Transition Temperature	-45	°C	ISO 6603-2
Thermal			
Vicat Softening Temperature, (A50)	147	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	98	°C	ISO 75B-1, -2

*)These are typical property values not to be construed as specification limits.

Processing Techniques

Users should determine the conditions necessary to obtain optimum product properties and suitability of the product for the intended application.

In cases where higher temperatures are required, please contact your appropriate technical contact for support.

Company Information

For further information regarding the Velogy, please visit <http://www.velogy.com>

© Rotterdam Olefins & Polyolefins B.V.

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, Velogy may further prohibit or restrict the sale of its products into certain applications.

For further information, please contact RegulatoryComplianceROP@velogy.com